



K-102 (99.93% Aluminum)		
基本型態	方形薄片	
長(mm)	1.0	
寬(mm)	1.0	
厚(μm)	25	
視密度 (g/cm ³)	0.32	
安息角 (degree)	44	
標準包裝 (lb/袋)	25	

K-202 (x) (99.9% Copper)		
基本型態	方形薄片	
長(mm)	0.6	
寬(mm)	0.6	
厚(μm)	25	
視密度 (g/cm ³)	0.95	
安息角 (degree)	TBD	
標準包裝 (lb/袋)	TBD	

K-109 (99.93% Aluminum)		
基本型態	方形薄片	
長(mm)	0.6	
寬(mm)	0.6	
厚(μm)	25	
視密度 (g/cm ³)	0.47	
安息角 (degree)	43	
標準包裝 (lb/袋)	25	

K-402 (x) (Bronze)		
基本型態	方形薄片	
長(mm)	1.0	
寬(mm)	1.0	
厚(μm)	25	
視密度 (g/cm ³)	0.95	
安息角 (degree)	TBD	
標準包裝 (lb/袋)	TBD	

K-107 (99.93% Aluminum)		
基本型態	平版纖維	
長(mm)	2.0	
寬(mm)	0.5	
厚(μm)	25	
視密度 (g/cm ³)	0.19	
安息角 (degree)	52	
標準包裝 (lb/袋)	20	

K-308 (x) (99.9% Zinc)		
基本型態	方形薄片	
長(mm)	0.6	
寬(mm)	0.6	
厚(μm)	25	
視密度 (g/cm ³)	1.1	
安息角 (degree)	43	
標準包裝 (lb/袋)	50	



T-101 (319 Aluminum)		
基本型態	蝌蚪狀	
長(mm)	1.4	
寬(mm)	-	
厚(μm)	600	
視密度 (g/cm ³)	1.57	
安息角 (degree)	32	
標準包裝 (lb/袋)	50	

S-201 (x) (99.8% Copper)		
基本型態	圓球狀	
長(mm)	N/A	
寬(mm)	N/A	
半徑(μm)	125	
視密度 (g/cm ³)	4.9	
安息角 (degree)	TBD	
標準包裝 (lb/袋)	TBD	

N-101 (99.93% Aluminum)		
基本型態	針狀	
長(mm)	4.8	
寬(mm)	-	
厚(μm)	500	
視密度 (g/cm ³)	1.26	
安息角 (degree)	45	
標準包裝 (lb/袋)	50	

R-601 (x) (Amorphous Steel)		
基本型態	帶狀	
長(mm)	21	
寬(mm)	1.6	
厚(μm)	50	
視密度 (g/cm ³)	TBD	
安息角 (degree)	TBD	
標準包裝 (lb/袋)	TBD	

樹脂基材	複合密度 g/cm ³	拉伸強度 MPa	收縮模數 GPa	體積百分率 %	SE (dB)
ABS	1.54	22.75	4.14	20	44
PC	1.54	44.13	6.55	20	46
ABS/PC	1.54	35.85	6.27	20	45
Nylon 6,6	1.48	65.50	8.27	22	40
PES	1.77	65.90	8.50	30	>50